

Grease wood paint alkyd resin								 86-750-3657002 doris@pjresin.com
Product Code	Non-volatile %	Viscosity mPa.s/25℃	Acid value mgKOH/g	Color (Fe-Co)	Solid hydroxyl value	Solvent	Properties	Applications
PJ2903-70	70±2	70000-90000	≤12	≤4	95±10	Xylene	Good flexibility and transparency	PU primer, nitro paint, tinted gold oil
PJ28005-70	70±2	50000-70000	≤12	≤4	130±10	Xylene/sec butyl ester	Good wettability dispersibility	
PJ11D-70K-1	70±2	20000-40000	≤10	≤4	105±10	Xylene	Low odour, good flexibility, good wettability	
PJ2806-70	70±2	50000-90000	≤14	≤3	100±10	Xylene/sec butyl ester	Good transparency and extinction	PU Primer, Matte Finish
PJ11-70D	70±2	70000-100000	≤12	≤2	110±10	Xylene/sec butyl ester	Fast drying,good extinction	
PJ2908-70	70±2	50000-80000	≤10	≤3	110±10	Xylene/Butyl ester	Low odour, fast drying, easy to polish, good matting	
PJ11-65B	65±2	13000-17000	≤10	≤3	120±10	Xylene/sec butyl ester	Fast drying, easy to polish, good transparency and good fullness	
PJ2816-70	70±2	70000-100000	≤12	≤2	130±10	Xylene/Butyl ester	Fast drying, high hardness, not easy to be tensioned and good matting	
PJ2905-70	70±2	70000-100000	≤10	≤3	125±10	Xylene/sec butyl ester	Good wettability, high fullness and transparency	PU Primer
PJ28003-70	70±2	80000-105000	≤12	≤2	130±10	Xylene/sec butyl ester	Fast drying and dilution resistance	
PJ11D-70K	70±2	70000-100000	≤12	≤4	110±10	Xylene/sec butyl ester	Quick drying, good wetting and easy polishing	
PJ11-70C	70±2	20000-50000	≤12	≤2	120±10	Xylene/sec butyl ester	Good versatility, high gloss and good fullness	PU glossy topcoat, nitro paint
PJ2816-70低粘	70±2	30000-45000	≤12	≤2	125±10	Xylene	Low odour, good extinction and good fullness	PU matte finish, nitro paint
PJ28202-70	70±2	15000-30000	≤10	≤2	110±10	Xylene/Butyl ester	Clear odor, good extinction and high hardness	Clear PU primer and finish
PJ28205-70	70±2	25000-55000	≤12	≤2	130±10	Xylene/Butyl ester	Clear odor, solvent release, good fullness and good extinction	
PJ28207-70	70±2	25000-55000	≤12	≤4	140±10	Xylene	Clear odor,high fullness and transparency	
PJ28301-65	65±2	20000-40000	≤10	≤3	135±10	Xylene	Excellent comprehensive performance, no residual odor	
*PJ2816-70A	70±2	50000-70000	≤12	≤2	115±10	Xylene/Butyl ester	Good transparency, high hardness, good extinction, fast odor elimination	
*PJ2807-65	65±2	5000-8000	≤12	≤4	135±10	Xylene/Butyl ester	Good fullness, good permeability, anti-subsidence and anti-tension reinforcement	PU primer and finish