

Curing agent & moisture curing resin

Product Code	Non-volatile %	Viscosity mPa.s/25°C	NCO %	Free TDI, %	Solvent	Properties	Applications
PJ01-60	60±2	40-150	10±1.2	≤2.0	EAC	Good universality, high hardness, good dryness and low free TDI.	PU polyester paint general curing agent
PJ01-50	50±2	13-24	9±1	≤1.6	EAC/BAC/XYL	Stable storage, good tightness, high hardness and good chemical resistance	
PJ01-50T	50±2	20-50	9±1	≤2.5	BAC	TDI trimer, fast drying, high hardness and good phase solubility	Universal curing agent added to improve dryness, hardness and mattness
PJ6803-60	60±2	50-150	6±1	≤0.5	EAC/BAC/PMA/DBE	Low free TDI, low viscosity and good workability. Full and bright paint film, high hardness. Excellent abrasion resistance, chemical resistance and good flexibility	Finishing varnish for bamboo and wood wares, wood floors, furniture and sealing primer for solid wood furniture
PJ6803-45	≥45	15-30	4±0.5	≤0.4	EAC/PMA/XYL/s-100/EAC/DBE/CYC		